



TOUGHOUY FLOATING TURBIDITY BARRIER TYPE 3.DOT SPECIFICATIONS

Fabric:18oz. nominal PVC coated polyesterBase Fabric (100% Polyester)Weight (FS-191-5041)Tensile Strength, Grab (ASTM 4632)Tear Strength, Tongue (ASTM 2261)Elongation (ASTM 4632)Adhesion Strength (ASTM 751)Abrasion Resistance (ASTM 4833)Hydrostatic Resistance (ASTM 751)UV Resistance (Weather-O-Meter)Cold Crack Resistance (ASTM 2136)High Temperature Resistance (ASTM 2136)Flame ResistanceSpecial Treatment(s)

1000D x 1000D / 9 x 9 18oz/yard² 325 lbs x 310 lbs 55 lbs x 45 lbs 21% x 21% 17x 17 lbs/inch 325 cycles At least 660 lbs/inch² Not excessive fading after 1000 HRS -40° F 180° F (Does not Block) Pass Anti Mildew



Geotextile: Woven filter fabric inserted into skirt of no less than 20% of skirt area

All main body seams are heat sealed. All geotextile seams are sewn double needle, black thread

5/8" diameter poly rope reinforced vertical edges

#5brass grommets

5/16" galvanized steel 7x19 load cable with PVC coating in top, 10,000 lb. break strength

5/16" galvanized chain ballast

Aluminum stress plates at cable and chain terminations

EPS flotation foam: 8" x 8" (standard. Increases to 10" x 10" and 12" x 12"- Based on curtain depth),

26.7 lb./ft. buoyancy in fresh water and 28.4 lb./ft. buoyancy in saltwater

MADE IN THE USA

SOLD ONLY BY AER-FLO DISTRIBUTORS